

O29. Iron electrowinning under alkaline conditions: effects of the current interruptions

Aleksey D. Lisenkov*, Daniela V. Lopes, Andrei V. Kovalevsky, Jorge R. Frade

*Department of Materials and Ceramic Engineering/ CICECO-Aveiro Institute of Materials,
University of Aveiro, 3810-193, Aveiro, Portugal*

* *lisenkov@ua.pt*

Nowadays, despite the rising demand of light materials, iron, namely steel, plays a crucial role in the modern world. For the time being, the main conclusion is that there are no economically feasible steelmaking technologies available that have the potential to meet the EU's climate and energy targets for 2030. At best, a 15% decrease in the overall CO₂ intensity of the sector could be achieved throughout the widespread dissemination of technologies that could reasonably become cost-effective in the future. Therefore, breakthrough technologies are urgent and indispensable. An electrochemically based route is being already developed as a candidate for an alternative to conventional steelmaking processes for CO₂-free iron production. Direct electrochemical reduction of iron oxides has been gaining attention as a process allowing in-situ reductions at the cathode, under strong alkaline media.

To find the feasibility of operation with long term interruptions (e.g. to seek preferential operation in low tariff periods), the experiments were performed with step changes in current rather than in potential. The selected experimental conditions comprise cycles with shut down interruptions, and other cycles with an impinged residual current (10%) to ensure cathodic protection. It seems that microstructural changes are the prevailing effect of interruption without cathodic protection in these ranges of potential/current density. Coarser grain sizes observed for unprotected shutdown interruptions may be related to surface re-structuring of the top layer, by re-oxidation during the unprotected interruption and subsequent reduction. Investigation of the cross-sections of the deposits in both regimes doesn't reveal any layer structure. The only deposit where layers were observed was obtained in the regime, where the cathodic protection step lasted 8 times longer than the deposition.